

# TEST REPORT

Report No.: AZT032212260008C-010

Page 1 of 12

**Applicant** : SIMCcom Wireless Solutions Limited.  
**Address** : SIMCom Headquarters Building, Building 3, No.289 Linhong Road,  
Changning District, Shanghai, China.  
**Manufacturer's name** : SIMCcom Wireless Solutions Limited.  
**Address** : SIMCom Headquarters Building, Building 3, No.289 Linhong Road,  
Changning District, Shanghai, China.

Report on the submitted samples said to be:

**Sample Name** : SIMCom Module  
**Trade Mark** : N/A  
**Tested model** : SIM8262E-M2  
**Series models** : N/A  
**Testing Period** : December 26, 2022 ~ December 30, 2022  
**Date of issue** : January 06, 2023  
**Results** : Please refer to next page(s).



## TEST REQUEST

## CONCLUSION

According to the customer's request, based on the performed tests on submitted sample, the result of Lead, Cadmium, Mercury, Hexavalent Chromium, PBBs, PBDEs, Dibutyl Phthalate (DBP), Benzyl butyl Phthalate (BBP), Bis(2-ethylhexyl) Phthalate (DEHP), Diisobutyl Phthalate (DIBP) content comply with the limit as set of RoHS Directive (EU) 2015/863 amending Annex II to Directive 2011/65/EU.

**Pass**

Signed for and on behalf of AZT

  
Suez Su  
Shenzhen AZT Technology Co., Ltd.  
深圳安正检测技术有限公司

No. 808, 924 Huaide Yinshan Building, 107 National Road, Fuwei Community, Fuyong Street, Baoan District, Shenzhen, Guangdong, China  
中国 广东省 深圳市宝安区福永街道福围社区 107 国道旁怀德银山大厦 808, 924  
Tel: 0755-23224560; E-mail: azt-ep@azt-tech.com; Http: www.azt-tech.com

# TEST REPORT

Report No.: AZT032212260008C-010

Page 2 of 12

## Results:

### A.EU RoHS Directive 2011/65/EU and its amendment directives on XRF

Test method: With reference to IEC 62321-3-1:2013, Screening by X-ray Fluorescence Spectroscopy (XRF)

| Seq. No. | Tested Part(s)                      | Results |    |    |     |      |       |
|----------|-------------------------------------|---------|----|----|-----|------|-------|
|          |                                     | Cd      | Pb | Hg | Cr▼ | Br▼  |       |
|          |                                     |         |    |    |     | PBBs | PBDEs |
| 1        | Silver sheet metal (optical module) | BL      | BL | BL | X   | /    | /     |
| 2        | Silver metal frame                  | BL      | BL | BL | BL  | /    | /     |
| 3        | Blue insulation                     | BL      | BL | BL | BL  | BL   | BL    |
| 4        | Transparent plastic film            | BL      | BL | BL | BL  | BL   | BL    |
| 5        | IC (Green PCB)                      | BL      | BL | BL | BL  | BL   | BL    |
| 6        | Gray IC (Green PCB)                 | BL      | BL | BL | X   | BL   | BL    |
| 7        | IC (Green PCB)                      | BL      | BL | BL | BL  | BL   | BL    |
| 8        | IC (Green PCB)                      | BL      | BL | BL | BL  | BL   | BL    |
| 9        | Patch capacitor (Green PCB)         | BL      | BL | BL | BL  | BL   | BL    |
| 10       | IC (Green PCB)                      | BL      | BL | BL | BL  | BL   | BL    |
| 11       | IC (Green PCB)                      | BL      | BL | BL | BL  | BL   | BL    |
| 12       | Crystal oscillator (Green PCB)      | BL      | BL | BL | BL  | /    | /     |
| 13       | Gray IC (Green PCB)                 | BL      | BL | BL | X   | BL   | BL    |
| 14       | Grey chip (Green PCB)               | BL      | BL | BL | BL  | BL   | BL    |
| 15       | Silver Metal (Green PCB)            | BL      | BL | BL | BL  | /    | /     |
| 16       | Patch capacitor (Green PCB)         | BL      | BL | BL | BL  | BL   | BL    |
| 17       | Blue chip (Green PCB)               | BL      | BL | BL | BL  | BL   | BL    |
| 18       | IC (Green PCB)                      | BL      | BL | BL | BL  | BL   | BL    |
| 19       | Green PCB                           | BL      | BL | BL | BL  | BL   | BL    |

\*\*\*\*\*



# TEST REPORT

Report No.: AZT032212260008C-010

Page 3 of 12

Note:

- (1) Results were obtained by XRF for primary screening, and further chemical testing by ICP (for Cd, Pb, Hg), UV-Vis (for Cr(VI)) and GC-MS (for PBBs, PBDEs) are recommended to be performed, if the concentration exceeds the below warning value according to IEC 62321-3-1:2013.

| Element | Unit  | Non-metal  | Metal  | Composite Material                               |
|---------|-------|--|--|--|
| Cd      | mg/kg | $BL \leq 70-3\sigma < X < 130+3\sigma \leq OL$   | $BL \leq 70-3\sigma < X < 130+3\sigma \leq OL$   | $BL \leq 50-3\sigma < X < 150+3\sigma \leq OL$   |
| Pb      | mg/kg | $BL \leq 700-3\sigma < X < 1300+3\sigma \leq OL$ | $BL \leq 700-3\sigma < X < 1300+3\sigma \leq OL$ | $BL \leq 500-3\sigma < X < 1500+3\sigma \leq OL$ |
| Hg      | mg/kg | $BL \leq 700-3\sigma < X < 1300+3\sigma \leq OL$ | $BL \leq 700-3\sigma < X < 1300+3\sigma \leq OL$ | $BL \leq 500-3\sigma < X < 1500+3\sigma \leq OL$ |
| Cr      | mg/kg | $BL \leq 700-3\sigma < X$                        | $BL \leq 700-3\sigma < X$                        | $BL \leq 500-3\sigma < X$                        |
| Br      | mg/kg | $BL \leq 300-3\sigma < X$                        | --   | $BL \leq 250-3\sigma < X$                        |

Note:

BL = Below Limit  
OL = Over Limit  
X = Inconclusive

\*\*\*\*\*



# TEST REPORT

Report No.: AZT032212260008C-010

Page 4 of 12

- (2) The XRF screening test for RoHS elements – The reading may be different to the actual content in the sample be of non-uniformity composition.
- (3) The maximum permissible limit is quoted from the document 2015/863/EC amending RoHS directive 2011/65/EU:
- (4) ▼ =For restricted substances PBBs and PBDEs, the results show the total Br content; The restricted substance was Cr (VI), and the results showed the total Cr content

| RoHS Restricted Substances             | Maximum Concentration Value (mg/kg)<br>(by weight in homogenous materials) |
|--|--|
| Cadmium (Cd)                           | 100  |
| Lead (Pb)                              | 1000   |
| Mercury (Hg)                           | 1000   |
| Hexavalent Chromium (Cr(VI))           | 1000   |
| Polybrominated biphenyls (PBBs)        | 1000   |
| Polybrominated diphenyl ethers (PBDEs) | 1000   |
| Dibutyl Phthalate (DBP)                | 1000   |
| Benzyl butyl Phthalate (BBP)           | 1000   |
| Bis(2-ethylhexyl) Phthalate (DEHP)     | 1000   |
| Diisobutyl Phthalate (DIBP)            | 1000   |

## Disclaimers:

This XRF Screening report is for reference purposes only. The applicant shall make its/his/her own judgment as to whether the information provided in this XRF screening report is sufficient for its/his/her purposes.

The result shown in this XRF screening report will differ based on various factors, including but not limited to, the sample size, thickness, area, surface flatness, equipment parameters and matrix effect (e.g. plastic, rubber, metal, glass, ceramic etc.). Further wet chemical pre-treatment with relevant chemical equipment analysis are required to obtain quantitative data.

\*\*\*\*\*





# TEST REPORT

Report No.: AZT032212260008C-010

Page 5 of 12

## **B. EU RoHS Directive 2011/65/EU and its amendment Directives 2015/863/EU on Lead, Cadmium, Mercury, Hexavalent Chromium, PBBs, PBDEs, DBP, BBP, DEHP, DIBP content.**

### Test method:

**Lead (Pb) & Cadmium (Cd) Content:**

With reference to IEC 62321-5:2013, by acid digestion and analysis was performed by inductively coupled plasma atomic emission spectrometer (ICP-OES)

**Mercury (Hg) Content:**

With reference to IEC 62321-4:2013+AMD1:2017 CSV, by acid digestion and analysis was performed by inductively coupled plasma atomic emission spectrometer (ICP-OES)

**Hexavalent Chromium (Cr<sup>6+</sup>) Content:**

With reference to IEC 62321-7-1:2015 or IEC 62321-7-2:2017, by alkaline digestion and analysis was performed by UV-visible spectrophotometer (UV-Vis)

**PBBs & PBDEs Content:**

With reference to IEC 62321-6:2015, by solvent extraction and analysis was performed by gas chromatographic-mass spectrometer (GC-MS)

**BBP DBP DEHP & DIBP Content:**

With reference to IEC 62321-8:2017, by solvent extraction and analysis was performed by gas chromatographic-mass spectrometer (GC-MS)

### **1) The test results of Hexavalent Chromium (Cr<sup>6+</sup>) (nonmetal)**

| Item                        | Unit  | MDL | Results |      | Limit |
|-----------------------------|-------|-----|---------|------|-------|
|                             |       |     | 6       | 13   |       |
| Hexavalent Chromium(Cr(VI)) | mg/kg | 8   | N.D.    | N.D. | 1000  |

### **2) The test results of Hexavalent Chromium (Cr<sup>6+</sup>) (metal)**

| Item                         | Unit               | MDL  | Results | Limit |
|------------------------------|--------------------|------|---------|-------|
|                              |                    |      | 1       |       |
| Hexavalent Chromium(Cr(VI))▼ | ug/cm <sup>2</sup> | 0.10 | N.D.    | --    |

\*\*\*\*\*



# TEST REPORT

Report No.: AZT032212260008C-010

Page 6 of 12

## Note:

- MDL = Method Detection Limit
- /= Not apply
- LOQ = Limit of Quantification, The LOQ of Hexavalent chromium is 0.10  $\mu\text{g}/\text{cm}^2$
- 0.1%=1000mg/kg
- N.D.=Not Detected (<MDL or LOQ)
- ▼ = a. The sample is positive for Cr (VI) if the Cr (VI) concentration is greater than 0.13 $\mu\text{g}/\text{cm}^2$ . The sample coating is considered to contain Cr (VI)  
 b. The sample is negative for Cr (VI) if Cr (VI) is N.D. (concentration less than 0.10 $\mu\text{g}/\text{cm}^2$ ). The sample coating is considered a non- Cr (VI) based coating  
 c. The result between 0.10 $\mu\text{g}/\text{cm}^2$  and 0.13 $\mu\text{g}/\text{cm}^2$  is considered to be inconclusive, unavoidable coating variations may influence the determination
- #1 According to RoHS directive 2011/65/EU and its amendments, Lead is exempted in glass of cathode ray tubes, electronic components and fluorescent tubes.
- #2 According to RoHS directive 2011/65/EU and its amendments, Lead is exempted in electronic ceramic parts (e.g. piezo electronic devices).
- #3 According to RoHS directive 2011/65/EU and its amendments, Lead is exempted as an alloying element in Copper containing up to 4% (40000ppm) by weight.
- #4 According to RoHS directive 2011/65/EU and its amendments, Lead is exempted in high melting temperature type solders (i.e. lead-based alloys containing 85 % by weight or more lead).
- #5 According to the statement provided by the customer, according to RoHS directive 2011/65/EU and its amendments, Lead is exempted as an alloying element in Aluminum containing up to 0.4% (4000ppm) by weight.
- #6 According to the statement provided by the customer, according to RoHS directive 2011/65/EU and its amendments, Cadmium and its compounds in electrical contact is exempted.
- #7 According to the statement provided by the customer, according to RoHS directive 2011/65/EU and its Amendments, Lead is exempted in steel for machining purposes and in galvanized steel containing up to 0.35% (3500ppm) by weight.

## 3) The test results of DBP, BBP, DEHP & DIBP

| Item                               | CAS No.  | Unit  | MDL | Results |      |      |      | Limit |
|------------------------------------|----------|-------|-----|---------|------|------|------|-------|
|                                    |          |       |     | 3       | 4    | 5    | 6    |       |
| Dibutyl Phthalate (DBP)            | 84-74-2  | mg/kg | 30  | N.D.    | N.D. | N.D. | N.D. | 1000  |
| Benzyl butyl Phthalate (BBP)       | 85-68-7  | mg/kg | 30  | N.D.    | N.D. | N.D. | N.D. | 1000  |
| Bis(2-ethylhexyl) Phthalate (DEHP) | 117-81-7 | mg/kg | 30  | N.D.    | N.D. | N.D. | N.D. | 1000  |
| Diisobutyl Phthalate (DIBP)        | 84-69-5  | mg/kg | 30  | N.D.    | N.D. | N.D. | N.D. | 1000  |

\*\*\*\*\*



# TEST REPORT

Report No.: AZT032212260008C-010

Page 7 of 12

| Item                               | CAS No.  | Unit  | MDL | Results |      |      |      | Limit |
|------------------------------------|----------|-------|-----|---------|------|------|------|-------|
|                                    |          |       |     | 7       | 8    | 9    | 10   |       |
| Dibutyl Phthalate (DBP)            | 84-74-2  | mg/kg | 30  | N.D.    | N.D. | N.D. | N.D. | 1000  |
| Benzyl butyl Phthalate (BBP)       | 85-68-7  | mg/kg | 30  | N.D.    | N.D. | N.D. | N.D. | 1000  |
| Bis(2-ethylhexyl) Phthalate (DEHP) | 117-81-7 | mg/kg | 30  | N.D.    | N.D. | N.D. | N.D. | 1000  |
| Diisobutyl Phthalate (DIBP)        | 84-69-5  | mg/kg | 30  | N.D.    | N.D. | N.D. | N.D. | 1000  |

| Item                               | CAS No.  | Unit  | MDL | Results |      |      |      | Limit |
|------------------------------------|----------|-------|-----|---------|------|------|------|-------|
|                                    |          |       |     | 11      | 13   | 14   | 16   |       |
| Dibutyl Phthalate (DBP)            | 84-74-2  | mg/kg | 30  | N.D.    | N.D. | N.D. | N.D. | 1000  |
| Benzyl butyl Phthalate (BBP)       | 85-68-7  | mg/kg | 30  | N.D.    | N.D. | N.D. | N.D. | 1000  |
| Bis(2-ethylhexyl) Phthalate (DEHP) | 117-81-7 | mg/kg | 30  | N.D.    | N.D. | N.D. | N.D. | 1000  |
| Diisobutyl Phthalate (DIBP)        | 84-69-5  | mg/kg | 30  | N.D.    | N.D. | N.D. | N.D. | 1000  |

| Item                               | CAS No.  | Unit  | MDL | Results |      |      | Limit |
|------------------------------------|----------|-------|-----|---------|------|------|-------|
|                                    |          |       |     | 17      | 18   | 19   |       |
| Dibutyl Phthalate (DBP)            | 84-74-2  | mg/kg | 30  | N.D.    | N.D. | N.D. | 1000  |
| Benzyl butyl Phthalate (BBP)       | 85-68-7  | mg/kg | 30  | N.D.    | N.D. | N.D. | 1000  |
| Bis(2-ethylhexyl) Phthalate (DEHP) | 117-81-7 | mg/kg | 30  | N.D.    | N.D. | N.D. | 1000  |
| Diisobutyl Phthalate (DIBP)        | 84-69-5  | mg/kg | 30  | N.D.    | N.D. | N.D. | 1000  |

## Remark:

- 0.1%=1000mg/kg
- N.D. = Not detected
- MDL= Method detected limited
- The samples were mixed for phthalic acid test
- Flow chart appendix is included
- Photo appendix is included.

\*\*\*\*\*



Shenzhen AZT Technology Co., Ltd.  
深圳安正检测技术有限公司

No. 808, 924 Huaide Yinshan Building, 107 National Road, Fuwei Community, Fuyong Street, Baoan District, Shenzhen, Guangdong, China  
中国 广东省 深圳市宝安区福永街道福围社区 107 国道旁怀德银山大厦 808, 924  
Tel: 0755-23224560; E-mail: azt-ep@azt-tech.com; Http: www.azt-tech.com


# TEST REPORT

Report No.: AZT032212260008C-010


Page 8 of 12

## Appendix


### 1. Test Flow chart for Cd/Pb /Hg content




### 2. Test Flowchart for Cr<sup>6+</sup> content (For non-metal material)



### Test Flowchart for Cr<sup>6+</sup> content (For metal material)



### 3. Test Flow chart for PBBs & PBDEs & DBP & BBP & DEHP & DIBP content



\*\*\*\*\*






# TEST REPORT

Report No.: AZT032212260008C-010

Page 9 of 12

The photo of the sample






# TEST REPORT

Report No.: AZT032212260008C-010

Page 10 of 12






# TEST REPORT

Report No.: AZT032212260008C-010

Page 11 of 12






# TEST REPORT

Report No.: AZT032212260008C-010

Page 12 of 12



AZT authenticate the photo on original report only

\*\*\*\*\* End of Report \*\*\*\*\*

## Statement:

1. The test report is considered invalidated without approval signature, special seal on the perforation.
2. The result(s) shown in this report refer only to the sample(s) tested.
3. Without written approval of AZT, this report can't be reproduced except in full.
4. The sample(s) and sample information was/were provided by the client who should be responsible for the authenticity which AZT hasn't verified.
5. In case of any discrepancy between the English version and Chinese version of the testing reports (if generated), the Chinese version shall prevail.

